


21049A-0.5

Version du
 12.06.2020



Compatibilité outil / matière
 Werkzeug / Werkstoffverträglichkeit
 Tool / Material compatibility




ESHOP / EZI CUT

- 1/3
- 2/3
- 3/3

EZI - ALPHA 3

Gruppe Vc [m/min]

| | | | | |
|--|--------------------------------|-----|-----|---|
| ACIERS ALLIÉS ET NON ALLIÉS UNLEGIERTE STÄHLE NON-ALLOYED STEELS | Rm < 450 N/mm ² | 1a | 120 | ● |
| | Rm 450 - 700 N/mm ² | 1b | 90 | ● |
| | Rm 700 - 900 N/mm ² | 1c | 60 | ● |
| | Rm < 1200 N/mm ² | 1d | 40 | ● |
| ACIERS INOX ROSTFREIE STÄHLE STAINLESS STEELS | Rm < 650 N/mm ² | 2a | 50 | ● |
| | Rm 650 - 950 N/mm ² | 2b | 40 | ● |
| | Rm > 950 N/mm ² | 2c | 30 | ● |
| ACIERS TREMPÉS GEHÄRTETE STÄHLE HARDENED STEELS | 44 - 56 HRC | 3a | 20 | ● |
| | 57 - 67 HRC | 3b | 15 | ● |
| MATÉRIAUX EXOTIQUES EXOTISCHE WERKSTOFFE EXOTIC MATERIALS | < 32 HRC | 4a | 30 | ● |
| | > 32 HRC | 4b | 15 | ● |
| GRAPHITE | | 5 | 105 | ● |
| FONTES GUSS CAST IRON | < 32 HRC | 6a | 45 | ● |
| | > 32 HRC | 6b | 35 | ● |
| TITANE TITAN | Rm < 800 N/mm ² | 7a | 40 | ● |
| | 800 < Rm N/mm ² | 7b | 30 | ● |
| ALLIAGES NICKEL NICKEL NICKEL ALLOYS | Rm < 1000 N/mm ² | 8a | 20 | ● |
| | 1000 < Rm N/mm ² | 8b | 15 | ● |
| CUIVRE, LAITON, BRONZE KUPFER, MESSING, BRONZE COPPER, BRASS, BRONZE | Rm < 850 N/mm ² | 9a | 180 | ● |
| | 850 < Rm N/mm ² | 9b | 150 | ● |
| ALUMINIUM | Si < 0.5% | 10a | 190 | ● |
| | 0.5% < Si < 5% | 10b | 150 | ● |
| | Si > 5% | 10c | 105 | ● |
| MATIÈRES SYNTHÉTIQUES KUNSTSTOFFE SYNTHETIC MATERIALS | Thermoplast | 11a | | |
| | Duraplast | 11b | | |
| MATIÈRES COMPOSITES FASERVERST. MATERIALIEN COMPOSITE MATERIALS | Fibre de verre | 12a | 95 | ● |
| | Fibre de carbone | 12b | 70 | ● |
| MÉTAUX PRÉCIEUX EDELMETALLE PRECIOUS MATERIALS | Or • Gold | 13a | 165 | ● |
| | Platine | 13b | 20 | ● |



| | |
|--------------|-------|
| D (0/- 0.01) | 0.5 |
| d (h5) | 3 |
| L | 38 |
| l1 | 0.75 |
| l3 | 6 |
| d3 | 0.45 |
| R | |
| e | |
| Z | 3 |
| Chanfrein | 0.012 |
| K | |
| w° collision | 6.6° |