

FRAISE POUR ALLIAGES RM < 1000
 FRÄSER FÜR WERKSTOFFE RM < 1000
 ENDMILL FOR ALLOYS RM < 1000

21138A-10

Version du
 12.06.2020



E2
 $\lambda = 48^\circ$
 $\gamma = 0^\circ$
0.05-0.15
45°
 l_1
1.5xD

Compatibilité outil / matière
 Werkzeug / Werkstoffverträglichkeit
 Tool / Material compatibility

- 1/3
- 2/3
- 3/3


EZI - ALPHA 3

Gruppe Vc [m/min]



ESHOP / EZI CUT

	Rm [N/mm ²]	Gruppe	Vc [m/min]	
ACIERS ALLIÉS ET NON ALLIÉS UNLEGIERTE STÄHLE NON-ALLOYED STEELS	Rm < 450 N/mm ²	1a	290	●
	Rm 450 - 700 N/mm ²	1b	220	●
	Rm 700 - 900 N/mm ²	1c	150	●
	Rm < 1200 N/mm ²	1d	90	●
ACIERS INOX ROSTFREIE STÄHLE STAINLESS STEELS	Rm < 650 N/mm ²	2a	90	●
	Rm 650 - 950 N/mm ²	2b	80	●
	Rm > 950 N/mm ²	2c	65	●
ACIERS TREMPÉS GEHÄRTETE STÄHLE HARDENED STEELS	44 - 56 HRC	3a	40	●
	57 - 67 HRC	3b	25	●
MATÉRIAUX EXOTIQUES EXOTISCHE WERKSTOFFE EXOTIC MATERIALS	< 32 HRC	4a	60	●
	> 32 HRC	4b	35	●
GRAPHITE		5		
FONTES GUSS CAST IRON	< 32 HRC	6a	150	●
	> 32 HRC	6b	115	●
TITANE TITAN	Rm < 800 N/mm ²	7a	80	●
	800 < Rm N/mm ²	7b	65	●
ALLIAGES NICKEL NICKEL NICKEL ALLOYS	Rm < 1000 N/mm ²	8a	40	●
	1000 < Rm N/mm ²	8b	30	●
CUIVRE, LAITON, BRONZE KUPFER, MESSING, BRONZE COPPER, BRASS, BRONZE	Rm < 850 N/mm ²	9a		
	850 < Rm N/mm ²	9b		
ALUMINIUM	Si < 0.5%	10a		
	0.5% < Si < 5%	10b		
	Si > 5%	10c		
MATIÈRES SYNTHÉTIQUES KUNSTSTOFFE SYNTHETIC MATERIALS	Thermoplast	11a		
	Duraplast	11b		
MATIÈRES COMPOSITES FASERVERST. MATERIALEN COMPOSITE MATERIALS	Fibre de verre	12a		
	Fibre de carbone	12b		
MÉTAUX PRÉCIEUX EDELMETALLE PRECIOUS MATERIALS	Or • Gold	13a		
	Platine	13b	40	●



D (h10)	10
d (h6)	10
L	72
l1	15
l3	
d3	
R	
e	
Z	4
Chanfrein	0.1
K	
w° collision	