

FRAISE Z4
FRÄSER Z4
ENDMILL Z4

22105A-16

Version du
21.01.2025




Compatibilité outil / matière
Werkzeug / Werkstoffverträglichkeit
Tool / Material compatibility

● 1/3
● 2/3
● 3/3

EZI - ALPHA 3

Groupe Vc [m/min]

ACIERS ALLIÉS ET NON ALLIÉS UNLEGIERTE STÄHLE NON-ALLOYED STEELS	Rm < 450 N/mm ²	1a	260	●
	Rm 450 - 700 N/mm ²	1b	150	●
	Rm 700 - 900 N/mm ²	1c	125	●
	Rm < 1200 N/mm ²	1d	75	●
ACIERS INOX ROSTFREIE STÄHLE STAINLESS STEELS	Rm < 650 N/mm ²	2a	84	●
	Rm 650 - 950 N/mm ²	2b	75	●
	Rm > 950 N/mm ²	2c	60	●
ACIERS TREMPÉS GEHÄRTETE STÄHLE HARDENED STEELS	44 - 56 HRC	3a		
	57 - 67 HRC	3b		
MATÉRIAUX EXOTIQUES EXOTISCHE WERKSTOFFE EXOTIC MATERIALS	< 32 HRC	4a		
	> 32 HRC	4b		
GRAPHITE		5	180	●
FONTES GUSS CAST IRON	< 32 HRC	6a	80	●
	> 32 HRC	6b	65	●
TITANE TITAN	Rm < 800 N/mm ²	7a	70	●
	800 < Rm N/mm ²	7b	50	●
ALLIAGES NICKEL NICKEL NICKEL ALLOYS	Rm < 1000 N/mm ²	8a		
	1000 < Rm N/mm ²	8b		
CUIVRE, LAITON, BRONZE KUPFER, MESSING, BRONZE COPPER, BRASS, BRONZE	Rm < 850 N/mm ²	9a	360	●
	850 < Rm N/mm ²	9b	250	●
ALUMINIUM	Si < 0.5%	10a	400	●
	0.5% < Si < 5%	10b	320	●
	Si > 5%	10c	250	●
MATIÈRES SYNTHÉTIQUES KUNSTSTOFFE SYNTHETIC MATERIALS	Thermoplast	11a		
	Duraplast	11b		
MATIÈRES COMPOSITES FASERVERST. MATERIALEN COMPOSITE MATERIALS	Fibre de verre	12a	160	●
	Fibre de carbone	12b	120	●
MÉTAUX PRÉCIEUX EDELMETALLE PRECIOUS MATERIALS	Or • Gold	13a	360	●
	Platine	13b	30	●



ESHOP / EZI CUT



D (h10)	16
d (h6)	16
L	92
l1	32
l3	
d3	
R	
e	
Z	4
Chanfrein	0.1
K	
w° collision	