

MICRO-FRAISE Z3 AVEC ARROSAGE CENTRAL  
 MIKROFRÄSER Z3 MIT INNENKÜHLUNG  
 MICRO ENDMILL Z3 WITH INTERNAL COOLING

28037A-2.0

Version du  
 20.01.2025



Compatibilité outil / matière  
 Werkzeug / Werkstoffverträglichkeit  
 Tool / Material compatibility



ESHOP / EZI CUT

● 1/3  
 ● 2/3  
 ● 3/3

EZI - ALPHA 3

Groupe Vc [m/min]

|                                                                            |                                |     |     |   |
|----------------------------------------------------------------------------|--------------------------------|-----|-----|---|
| ACIERS ALLIÉS ET NON ALLIÉS<br>UNLEGIERTE STÄHLE<br>NON-ALLOYED STEELS     | Rm < 450 N/mm <sup>2</sup>     | 1a  | 310 | ● |
|                                                                            | Rm 450 - 700 N/mm <sup>2</sup> | 1b  | 180 | ● |
|                                                                            | Rm 700 - 900 N/mm <sup>2</sup> | 1c  | 150 | ● |
|                                                                            | Rm < 1200 N/mm <sup>2</sup>    | 1d  | 90  | ● |
| ACIERS INOX<br>ROSTFREIE STÄHLE<br>STAINLESS STEELS                        | Rm < 650 N/mm <sup>2</sup>     | 2a  | 120 | ● |
|                                                                            | Rm 650 - 950 N/mm <sup>2</sup> | 2b  | 100 | ● |
|                                                                            | Rm > 950 N/mm <sup>2</sup>     | 2c  | 90  | ● |
| ACIERS TREMPÉS GEHÄRTETE<br>STÄHLE HARDENED STEELS                         | 44 - 56 HRC                    | 3a  | 50  | ● |
|                                                                            | 57 - 67 HRC                    | 3b  | 30  | ● |
| MATÉRIAUX EXOTIQUES<br>EXOTISCHE WERKSTOFFE<br>EXOTIC MATERIALS            | < 32 HRC                       | 4a  | 60  | ● |
|                                                                            | > 32 HRC                       | 4b  | 30  | ● |
| GRAPHITE                                                                   |                                | 5   | 210 | ● |
| FONTES GUSS CAST IRON                                                      | < 32 HRC                       | 6a  | 90  | ● |
|                                                                            | > 32 HRC                       | 6b  | 70  | ● |
| TITANE TITAN                                                               | Rm < 800 N/mm <sup>2</sup>     | 7a  | 90  | ● |
|                                                                            | 800 < Rm N/mm <sup>2</sup>     | 7b  | 60  | ● |
| ALLIAGES NICKEL<br>NICKEL<br>NICKEL ALLOYS                                 | Rm < 1000 N/mm <sup>2</sup>    | 8a  | 40  | ● |
|                                                                            | 1000 < Rm N/mm <sup>2</sup>    | 8b  | 30  | ● |
| CUIVRE, LAITON, BRONZE<br>KUPFER, MESSING, BRONZE<br>COPPER, BRASS, BRONZE | Rm < 850 N/mm <sup>2</sup>     | 9a  | 430 | ● |
|                                                                            | 850 < Rm N/mm <sup>2</sup>     | 9b  | 300 | ● |
| ALUMINIUM                                                                  | Si < 0.5%                      | 10a | 480 | ● |
|                                                                            | 0.5% < Si < 5%                 | 10b | 380 | ● |
|                                                                            | Si > 5%                        | 10c | 300 | ● |
| MATIÈRES SYNTHÉTIQUES<br>KUNSTSTOFFE<br>SYNTHETIC MATERIALS                | Thermoplast                    | 11a |     | ● |
|                                                                            | Duraplast                      | 11b |     | ● |
| MATIÈRES COMPOSITES<br>FASERVERST. MATERIALEN<br>COMPOSITE MATERIALS       | Fibre de verre                 | 12a | 190 | ● |
|                                                                            | Fibre de carbone               | 12b | 140 | ● |
| MÉTAUX PRÉCIEUX<br>EDELMETALLE<br>PRECIOUS MATERIALS                       | Or • Gold                      | 13a | 430 | ● |
|                                                                            | Platine                        | 13b | 40  | ● |



|              |      |
|--------------|------|
| D (0/-0.02)  | 2    |
| d (h5)       | 3    |
| L            | 38   |
| l1           | 4.5  |
| l3           |      |
| d3           |      |
| R            |      |
| e            |      |
| Z            | 3    |
| Chanfrein    |      |
| K            |      |
| w° collision | 4.5° |