

RONDELLE-MD-H1S-BRUT-DE-FRITTAGE · SAW-BLANKS-SC-H1S-JUST-SINTERED · RONDEN-HM-H1S-ROH-GESINTERT



SWISS MADE

20150-25-5-2.3 Version 11.09.2026

H1S

UNIVERSAL GRADE WITH GOOD WEAR RESISTANCE

MATERIAL COMPATIBILITY

●●● Excellent (3/3) ●●○ Good (2/3) ●○○ Possible (1/3) ○○○ Not recommended

Product material compatibility				
CATEGORY	MATERIAL	SPECIFICATION	GRP	20150-25-5-2.3
Alloyed and non-alloyed steels	Non-alloyed steels	Rm < 450 N/mm²	1a	○○○ 0/3
		Rm 450–700 N/mm²	1b	○○○ 0/3
		Rm 700–900 N/mm²	1c	○○○ 0/3
		Rm > 1200 N/mm²	1d	○○○ 0/3
Stainless steels	Stainless steels	Rm < 650 N/mm²	2a	○○○ 0/3
		Rm 650–950 N/mm²	2b	○○○ 0/3
		Rm > 950 N/mm²	2c	○○○ 0/3
Hardened steels	Hardened steels	44–56 HRC	3a	○○○ 0/3
		57–67 HRC	3b	○○○ 0/3
Exotic materials	Special alloys	< 32 HRC	4a	○○○ 0/3
		> 32 HRC	4b	○○○ 0/3
Graphite	Industrial graphite		5	○○○ 0/3
Cast iron	Grey / nodular cast iron	< 32 HRC	6a	○○○ 0/3
		> 32 HRC	6b	○○○ 0/3
Titanium	Titanium alloys	Rm < 600 N/mm²	7a	○○○ 0/3
		600 < Rm N/mm²	7b	○○○ 0/3
Nickel alloys	Inconel, Hastelloy	Rm < 1000 N/mm²	8a	○○○ 0/3
		Rm > 1000 N/mm²	8b	○○○ 0/3
Copper, brass, bronze	Copper-based	Rm < 850 N/mm²	9a	○○○ 0/3
		Rm > 850 N/mm²	9b	○○○ 0/3
Aluminum	Aluminum alloys	Si < 0.5%	10a	○○○ 0/3
		0.5% < Si < 5%	10b	○○○ 0/3
		Si > 5%	10c	○○○ 0/3
Synthetic materials	Engineering plastics	Thermoplastic	11a	○○○ 0/3
		Thermoset	11b	○○○ 0/3
Composite materials	Reinforced composites	Glass fiber / GFK	12a	○○○ 0/3
		Carbon fiber / KFK	12b	○○○ 0/3
Precious metals	Gold, platinum, silver	Gold	13a	○○○ 0/3
		Platinum	13b	○○○