

MICRO-FRAISE-HÉMISPHERIQUE Z2 · BALL-NOSE-
MICRO-ENDMILL Z2 · MICRO-FRÄSER-HALBRUND Z2



21082D-1.4 Version 11.09.2026



E25
UF

ULTRAFINE GRADE HIGH-END GRADE WITH VERY HIGH HARDNESS AND TOUGHNESS FOR MICRO-MACHINING

$\lambda = 30^\circ$
 $\gamma = 10^\circ$

HELIX ANGLE 30° AND CUTTING ANGLE 10°

HEMISPHERICAL SHAPE

SIDE AND CENTER CUT

l_1
3xD

CUTTING EDGE LENGTH 3xD


FITTING LENGTH LONG

MATERIAL COMPATIBILITY

●●● Excellent (3/3) ●●○ Good (2/3) ●○○ Possible (1/3) ○○○ Not recommended

Product material compatibility				
CATEGORY	MATERIAL	SPECIFICATION	GRP	21082D-1.4
Alloyed and non-alloyed steels	Non-alloyed steels	Rm < 450 N/mm²	1a	○○○ 0/3
		Rm 450–700 N/mm²	1b	○○○ 0/3
		Rm 700–900 N/mm²	1c	○○○ 0/3
		Rm > 1200 N/mm²	1d	○○○ 0/3
Stainless steels	Stainless steels	Rm < 650 N/mm²	2a	○○○ 0/3
		Rm 650–950 N/mm²	2b	○○○ 0/3
		Rm > 950 N/mm²	2c	○○○ 0/3
Hardened steels	Hardened steels	44–56 HRC	3a	○○○ 0/3
		57–67 HRC	3b	○○○ 0/3
Exotic materials	Special alloys	< 32 HRC	4a	○○○ 0/3
		> 32 HRC	4b	○○○ 0/3
Graphite	Industrial graphite		5	●●● 3/3
Cast iron	Grey / nodular cast iron	< 32 HRC	6a	○○○ 0/3
		> 32 HRC	6b	○○○ 0/3
Titanium	Titanium alloys	Rm < 600 N/mm²	7a	○○○ 0/3
		600 < Rm N/mm²	7b	○○○ 0/3
Nickel alloys	Inconel, Hastelloy	Rm < 1000 N/mm²	8a	○○○ 0/3
		Rm > 1000 N/mm²	8b	○○○ 0/3
Copper, brass, bronze	Copper-based	Rm < 850 N/mm²	9a	●●○ 2/3
		Rm > 850 N/mm²	9b	●●○ 2/3
Aluminum	Aluminum alloys	Si < 0.5%	10a	●○○ 1/3
		0.5% < Si < 5%	10b	●●○ 2/3
		Si > 5%	10c	●●● 3/3
Synthetic materials	Engineering plastics	Thermoplastic	11a	○○○ 0/3
		Thermoset	11b	○○○ 0/3
Composite materials	Reinforced composites	Glass fiber / GFK	12a	●●● 3/3
		Carbon fiber / KFK	12b	●●● 3/3
Precious metals	Gold, platinum, silver	Gold	13a	●○○ 1/3
		Platinum	13b	●●● 3/3

TECHNICAL DRAWING



DIMENSIONS

NOMINAL DIMENSIONS	
D (0 / -0.01)	1.4 mm
d (h5)	3 mm
L	38 mm
l1	4 mm
l3	–
d3	–
R	0.7 mm
e	–
Z	2
Chamfer K	–
w° collision angle	6.4°



E-SHOP / EZI CUT
eskenazi.ch/eshop/21082D-1.4

© 2026 Eskenazi SA — Carouge, Genève
All rights reserved